



A Division of California Products • An Employee Owned Company  
150 Dascomb Road, Andover Massachusetts 01810 USA  
Phone: 978-623-9980 / 800-225-1141 • Fax: 978-623-9960  
www.plexipave.com • info@plexipave.com

## **SECTION 10.6**

### **SITE IMPROVEMENTS** **ATHLETIC FACILITIES**

EXTERIOR/INTERIOR

ACRYLIC LATEX

PLEXIPAVE®

CLEAR TOPCOAT

### **CLEAR-GLO #3**

#### **DESCRIPTION:**

Clear-Glo #3 is a clear acrylic surface sealer designed as a companion product for the Plexipave Color Finish System. When applied as a surface finish over the Plexipave Color Finish System, Clear-Glo #3 provides a light sheen finish and extends the life of the Plexipave System and the life of playing lines where dust and wear are a problem. Clear-Glo #3 may also be used to replace part of the water in mixing Plexipave or Fortified Plexipave on Indoor tennis Courts only.

#### **SURFACE USES:**

- Over the Plexipave System where it is subjected to heavy foot traffic such as walkways, playgrounds and heavily used public basketball courts.

#### **APPLICATION:**

- Dilute with equal amount of water (1:1) before using; mix well before using.
- One coat is usually sufficient – Two coats for extreme wear areas.
- Applied by using a squeegee followed by a wide hair-type pushbroom. On smaller surface areas, apply by using a brush or lamb's wool applicator.
- When adding to Plexipave or Fortified Plexipave, replace only a portion of the water in the mix with Clear-Glo #3 (For Indoor Courts only).

#### **DRYING TIME:**

- Approximately 1 hour for each coat.

#### **COLOR RANGE:**

- Clear – light sheen finish

#### **COVERAGE:**

- 40 square yards per gallon per coat (.025 gal/sq. yd.).

#### **LIMITATIONS:**

- Apply only when ambient temperature is 50°F and rising.
- Do not allow to puddle. Apply evenly and lightly.
- Do not apply during rainfall or when rain is imminent.
- Surface should be clean and free of dust before applying.
- Do not apply on wood surfaces.
- Do not shake; stir only.
- Keep from freezing - Do not store in the hot sun – Keep container tightly closed when not in use.
- Do not add Clear-Glo #3 to the Plexipave mix when heavy traffic is expected. Apply one or two coats.
- Do not apply if surface temperature is above 140°F.
- The Plexipave System will not prevent surface or structural cracks from reoccurring.

