

PRODUCT DATA & SPECIFICATION

SITE IMPROVEMENTS
ATHLETIC FACILITIES

RECOMMENDED PAVING MIXTURES FOR TENNIS COURTS

SUB-GRADE:

Granular fill as needed for stability and slope.

BASE COURSE:

A minimum of 4" dense graded crushed aggregate properly compacted. Finish tolerance $\pm 1/2"$ in 10' (95% minimum of laboratory density).

BINDER OR LEVELING COURSE (Hot Mix Asphalt):

The binder or leveling course shall be a minimum of 1 1/2" thick. The surface tolerance after completion shall be $\pm 1/4"$ in 10'.

Sieve Sizes:

<i>Square Openings</i>	<i>Percentage Passing</i>
1"	100
3/4"	90-100
3/8"	65-80
<u>#4</u>	<u>46-60</u>
#8	35-45
#30	17-29
#200	2-7
A.C. (% of mix)	5.5-7.5

SURFACE COURSE (Hot Mix Asphalt):

The surface course shall be a minimum of 1" thick. The surface tolerance after completion shall be $\pm 1/8"$ when measured in any direction with a 10' straightedge.

Sieve Sizes:

<i>Square Openings</i>	<i>Percentage Passing</i>
1/2"	100
3/8"	90-100
<u>#4</u>	<u>63-78</u>
#8	50-60
#30	25-42
#200	3/8
A.C. (% of mix)	7.5-9.5
A.C. 20 or 30	

Voids content less than 9%

8/04



A Division of California Products
An Employee Owned Company

150 Dascomb Road, Andover MA 01810 USA • www.plexipave.com • info@plexipave.com
Telephone: 1-978-623-9980 / 1-800-225-1141 • Fax: 1-978-623-9960